



INVICTUS

MAXIMUS

CLICK 55



## Specification

Description	Rigid core SPC with sound insulating underlay attached	
Thickness	EN ISO 24346	6.00 mm
Wearlayer	EN ISO 24340	0.55 mm
Weight per sqm	EN ISO 23997	9820 g/m <sup>2</sup>
Surface PUR coating	Scratchmaster® top layer	
Locking System	Unilin's Unipush® click technology	
Classification	EN ISO 10874	23 Domestic Heavy - 33 Commercial Heavy - 42 Industrial General

## Performance

Reaction to fire	EN 13501-1	BF-S1
Slip resistance	EN 13893	DS
Slip resistance (dynamic coefficient of friction)	DIN 51130	R10
Thermal resistance (R value)	EN 12664	0.048 (m <sup>2</sup> .K)/W
Thermal conductivity	EN 12664	0.124 (W/m.K)
Underfloor heating	EN ISO 12524	Yes, max. 27°C
Electrostatic performance (antistatic)	EN 1815	< 2 kV
Residual indentation	EN ISO 24343-1	<0.1 mm
Dimensional stability	EN ISO 23999	≤ 0.15%
Dimensional stability (curling)	EN ISO 23999	pass
Castor chair resistance	EN ISO 4918	pass, Type W
Colour fastness	EN ISO 105-B02	>6
Impact sound insulation	EN ISO 717-2 (ΔLw)	20dB
Chemical / Stain resistance	EN ISO 26987	pass
Abrasion resistance	EN ISO 660-1	class T
French VOC regulation	ISO 16000	A+
Indoor AIR quality	ISO 16000	Greenguard GOLD
Indoor AIR quality		Floorscore
Content of pentachlorophenol		PCP under detection limit
Formaldehyde emissions	EN ISO 717-1 (28 days test)	NA HCHO (has not been added)
Phthalate free		Yes, biobased
CE marking	EN 14041:2011	

## Packaging

		Size plank / tile	Pieces / carton
Size and packaging wood	EN ISO 24342	178x1213 mm (7"x47.75")	8 planks / carton = 1.725 m <sup>2</sup> (18.57 ft <sup>2</sup> ) / carton
Size and packaging stone	EN ISO 24342	298x603 mm (11.75"x23.75")	8 tiles / carton = 1.440 m <sup>2</sup> (15.503 ft <sup>2</sup> ) / carton

## Warranty

Warranty	25 years Residential - 15 years Commercial
----------	--

The technical data is correct at the time of printing. 07/2023



**INVICTUS MAXIMUS CLICK 55 (SPC click) - LIGHT REFLECTION VALUE** BS.8493:2008+A1:2010.

DESSIN	LRV
Highland Oak Classic	23.8
Highland Oak Roasted	15.3
Highland Oak Chocolate	11.5
Highland Oak Canyon	23.4
Highland Oak Ebony New	12.8
Highland Oak Frosted	25.6
Highland Oak Sunrise	38.9
New England Oak Dusk	18.5
New England Oak Misty	26.4
New England Oak Sand	22.1
New England Oak Toffee	12.0
Norwegian Wood Arctic	40.6
Norwegian Wood Fjord	23.6
Norwegian Wood Barrel	9.9
Norwegian Wood Thunder	15.2
French Oak Polar	47.1
French Oak Linen	27.9
French Oak Desert	26.8
French Oak Sun	23.5
French Oak Storm	29.8

DESSIN	LRV
Groovy Granite Alabaster	53.2
Groovy Granite Shadow	30.4
Groovy Granite Steel	30.1
Groovy Granite Lava	14.5

**INVICTUS MAXIMUS (SPC) CLICK - SLIP RESISTANCE** Pendulum test values - BS 7976-2

TYPE	DESIGN	DRY		WET	
		Lowest Test Value	Slip Risk Class	Lowest Test Value	Slip Risk Class
WOOD	FRENCH OAK	64	LOW	37	LOW
WOOD	HIGHLAND OAK	71	LOW	38	LOW
WOOD	NEW ENGLAND OAK	59	LOW	33	MODERATE
WOOD	NORWEGIAN WOOD	60	LOW	42	LOW
STONE	GROOVY GRANITE	64	LOW	33	MODERATE

